

Technical Data Sheet

Product name: E-PVC release film embossed

Description: **Grade:** AD-M240/13
Color: transparent, or coloured as per order
Surface: 624_0

Properties	Standard	Unit	Values
Thickness (calculated)	ISO 4593 DIN 53370	µm	45 ± 10 %
Density transparent (13/0000)	DIN EN ISO 1183-2	g/cm ³	1,37 ± 0,02
Weight per unit area [45 µm]	DIN EN ISO 2286-2	g/m ²	62 ± 10 %
Material Yield [45 µm]		m ² /kg	16 ± 10 %
White opaque [03/402B]	DIN EN ISO 1183-2	g/cm ³	1,42 ± 0,02
Yellow [13/924B]	DIN EN ISO 1183-2	g/cm ³	1,41 ± 0,02

Thickness flat/flat	After Embossing	µm	310 ± 10 %
---------------------	-----------------	----	------------

Maximum reel width others on request		mm	< 1500
Maximum reel diameter others on request		mm	< 660

Regulatory:

The product corresponds to:
 ▪ Package requirements for heavy metals
 Supplementary confirmations to the above named points can be issued on request.

Storage conditions:

- Do not store at temperatures above 32°C (90°F)
 - Do not expose to rapid temperature changes or direct sunlight
 - Ideal storage humidity is 40-70% RH
 - Condition film a minimum of 24 hours at ambient room temperature before use
 - Store rolls in original packaging
- Use material within one year of production date

